PCT

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ^{6} : C30B 15/00, 33/00, 29/06	A1	(11) International Publication Number: WO 98/45509
		(43) International Publication Date: 15 October 1998 (15.10.98)

(21) International Application Number: PCT/US98/07305

(22) International Filing Date: 9 April 1998 (09.04.98)

(30) Priority Data:
60/041,845   9 April 1997 (09.04.97)   US

(71) Applicant: MEMC ELECTRONIC MATERIALS, INC. [US/US]; 501 Pearl Drive, P.O. Box 8, St. Peters, MO 63376 (US).

(72) Inventors: FALSTER, Robert; Via Caradosso, 11, I–20123 Milano (IT). HOLZER, Joseph, C.; 5234 Gutermuth Road, St. Charles, MO 63304 (US).

(74) Agents: HEJLEK, Edward, J. et al.; Senniger, Powers, Leavitt & Roedel, 16th floor, One Metropolitan Square, St. Louis, MO 63102 (US).

(81) Designated States: CN, JP, KR, SG, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

(54) Title: LOW DEFECT DENSITY SILICON

(57) Abstract

The present invention relates to single crystal silicon, in ingot or wafer form, which contains an axially symmetric region which is free of agglomerated intrinsic point defects, and a process for the preparation thereof. The process comprises controlling growth conditions, such as growth velocity, v, instantaneous axial temperature gradient, G_0, and the cooling rate, within a range of temperatures at which silicon self–interstitials are mobile, in order to prevent the formation of these agglomerated defects. In ingot form, the axially symmetric region has a width, as measured from the circumferential edge of the ingot radially toward the central axis, which is at least about 30 % the length of the radius of the ingot. The axially symmetric region additionally has a length, as measured along the central axis, which is at least about 20 % the length of the constant diameter portion of the ingot.

3

crystal originated Light Point Defects (LPDs), as well as certain classes of bulk defects observed by infrared light scattering techniques such as Scanning Infrared Microscopy and Laser Scanning Tomography. Also present

5 in regions of excess vacancies are defects which act as the nuclei for ring oxidation induced stacking faults (OISF). It is speculated that this particular defect is a high temperature nucleated oxygen agglomerate catalyzed by the presence of excess vacancies.

10 Defects relating to self-interstitials are less well studied. They are generally regarded as being low densities of interstitial-type dislocation loops or networks. Such defects are not responsible for gate oxide integrity failures, an important wafer performance

15 criterion, but they are widely recognized to be the cause of other types of device failures usually associated with current leakage problems.

The density of such vacancy and self-interstitial agglomerated defects in Czochralski silicon is

20 conventionally within the range of about $1*10^3$/cm^3 to about $1*10^7$/cm^3. While these values are relatively low, agglomerated intrinsic point defects are of rapidly increasing importance to device manufacturers and, in fact, are now seen as yield-limiting factors in device

25 fabrication processes.

To date, there generally exists three main approaches to dealing with the problem of agglomerated intrinsic point defects. The first approach includes methods which focus on crystal pulling techniques in

30 order to reduce the number density of agglomerated intrinsic point defects in the ingot. This approach can be further subdivided into those methods having crystal pulling conditions which result in the formation of vacancy dominated material, and those methods having

35 crystal pulling conditions which result in the formation of self-interstitial dominated material. For example, it

4

has been suggested that the number density of
agglomerated defects can be reduced by (i) controlling
v/G_0 to grow a crystal in which crystal lattice vacancies
are the dominant intrinsic point defect, and (ii)

5   influencing the nucleation rate of the agglomerated
defects by altering (generally, by slowing down) the
cooling rate of the silicon ingot from about 1100°C to
about 1050°C during the crystal pulling process. While
this approach reduces the number density of agglomerated

10   defects, it does not prevent their formation. As the
requirements imposed by device manufacturers become more
and more stringent, the presence of these defects will
continue to become more of a problem.

       Others have suggested reducing the pull rate, during

15   the growth of the body of the crystal, to a value less
than about 0.4 mm/minute. This suggestion, however, is
also not satisfactory because such a slow pull rate leads
to reduced throughput for each crystal puller. More
importantly, such pull rates lead to the formation of

20   single crystal silicon having a high concentration of
self-interstitials. This high concentration, in turn,
leads to the formation of agglomerated self-interstitial
defects and all the resulting problems associated with
such defects.

25   A second approach to dealing with the problem of
agglomerated intrinsic point defects includes methods
which focus on the dissolution or annihilation of
agglomerated intrinsic point defects subsequent to their
formation. Generally, this is achieved by using high

30   temperature heat treatments of the silicon in wafer form.
For example, Fusegawa et al. propose, in European Patent
Application 503,816 A1, growing the silicon ingot at a
growth rate in excess of 0.8 mm/minute, and heat treating
the wafers which are sliced from the ingot at a

35   temperature in the range of 1150°C to 1280°C to
annihilate the defects which form during the crystal

5

growth process. Such heat treatments have been shown to
reduce the defect density in a thin region near the wafer
surface. The specific treatment needed will vary
depending upon the concentration and location of
5   agglomerated intrinsic point defects in the wafer.
Different wafers cut from a crystal which does not have a
uniform axial concentration of such defects may require
different post-growth processing conditions.
Furthermore, such wafer heat treatments are relatively
10   costly, have the potential for introducing metallic
impurities into the silicon wafers, and are not
universally effective for all types of crystal-related
defects.

A third approach to dealing with the problem of
15   agglomerated intrinsic point defects is the epitaxial
deposition of a thin crystalline layer of silicon on the
surface of a single crystal silicon wafer. This process
provides a single crystal silicon wafer having a surface
which is substantially free of agglomerated intrinsic
20   point defects. Epitaxial deposition, however,
substantially increases the cost of the wafer.

In view of these developments, a need continues to
exist for a method of single crystal silicon preparation
which acts to prevent the formation of agglomerated
25   intrinsic point defects by suppressing the agglomeration
reactions which produce them. Rather than simply
limiting the rate at which such defects form, or
attempting to annihilate some of the defects after they
have formed, a method which acts to suppress
30   agglomeration reactions would yield a silicon substrate
that is substantially free of agglomerated intrinsic
point defects. Such a method would also afford single
crystal silicon wafers having epi-like yield potential,
in terms of the number of integrated circuits obtained
35   per wafer, without having the high costs associated with
an epitaxial process.

6

SUMMARY OF THE INVENTION

Among the objects of the present invention,
therefore, is the provision of single crystal silicon in
ingot or wafer form having an axially symmetric region of
5   substantial radial width which is substantially free of
defects resulting from an agglomeration of crystal
lattice vacancies or silicon self-interstitials; and the
provision of a process for preparing a single crystal
silicon ingot in which the concentration of vacancies and
10   self-interstitials is controlled in order to prevent an
agglomeration of intrinsic point defects in an axially
symmetric segment of a constant diameter portion of the
ingot, as the ingot cools from the solidification
temperature.

15   Briefly, therefore, the present invention is
directed to a single crystal silicon wafer having a
central axis, a front side and a back side which are
generally perpendicular to the axis, a circumferential
edge, and a radius extending from the central axis to the
20   circumferential edge. The wafer comprises an axially
symmetric region which is substantially free of
agglomerated intrinsic point defects. The axially
symmetric region extends radially inwardly from the
circumferential edge of the wafer and has a width, as
25   measured from the circumferential edge radially toward
the central axis, which is at least about 40% of the
length of the radius of the wafer.

The present invention is further directed to a
single crystal silicon ingot having a central axis, a
30   seed-cone, an end-cone, and a constant diameter portion
between the seed-cone and the end-cone which has a
circumferential edge and a radius extending from the
central axis to the circumferential edge. The single
crystal silicon ingot is characterized in that, after
35   ingot growth is complete and the ingot has cooled from
the solidification temperature, the constant diameter

7

portion contains an axially symmetric region which is
substantially free of agglomerated intrinsic point
defects. The axially symmetric region extends radially
inwardly from the circumferential edge and has a width,
as measured from the circumferential edge radially toward
the central axis, which is at least about 30% of the
length of the radius of the constant diameter portion.
The axially symmetric region also has a length, as
measured along the central axis, of at least about 20% of
the length of the constant diameter portion of the ingot.

The present invention is still further directed to a
process for growing a single crystal silicon ingot in
which an ingot, comprising a central axis, a seed-cone,
an end-cone and a constant diameter portion between the
seed-cone and the end-cone which has a circumferential
edge and a radius extending from the central axis to the
circumferential edge, is grown from a silicon melt and
then cooled from the solidification temperature in
accordance with the Czochralski method. The process
comprises controlling a growth velocity, v, and an
instantaneous axial temperature gradient, G_0, of the
crystal during growth of the constant diameter portion to
cause the formation of an axially symmetric region which,
upon cooling the ingot from the solidification
temperature, is substantially free of agglomerated
intrinsic point defects. The axially symmetric region
extends radially inwardly from the circumferential edge,
has a width as measured from the circumferential edge
radially toward the central axis which is at least about
30% of the length of the radius of the constant diameter
portion, and a length as measured along the central axis
of at least about 20% of the length of the constant
diameter portion.

Other objects and features of this invention will be
in part apparent and in part pointed out hereinafter.

8

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a graph which shows an example of how the initial concentration of self-interstitials, [I], and vacancies, [V], changes with an increase in the value of
5   the ratio v/G_0, where v is the growth rate and G_0 is the instantaneous axial temperature gradient.

FIG. 2 is a graph which shows an example of how ΔG_I, the change in free energy required for the formation of agglomerated interstitial defects, increases as the
10   temperature, T, decreases, for a given initial concentration of self-interstitials, [I].

FIG. 3 is a graph which shows an example of how ΔG_I, the change in free energy required for the formation of agglomerated interstitial defects, decreases (as the
15   temperature, T, decreases) as a result of the suppression of the concentration of self-interstitials, [I], through the means of radial diffusion. The solid line depicts the case for no radial diffusion whereas the dotted line includes the effect of diffusion.

20   FIG. 4 is a graph which shows an example of how ΔG_I, the change in free energy required for the formation of agglomerated interstitial defects, is sufficiently decreased (as the temperature, T, decreases), as a result of the suppression of the concentration of self-
25   interstitials, [I], through the means of radial diffusion, such that an agglomeration reaction is prevented. The solid line depicts the case for no radial diffusion whereas the dotted line includes the effect of diffusion.

30   FIG. 5 is a graph which shows an example of how the initial concentration of self-interstitials, [I], and vacancies, [V], can change along the radius of an ingot or wafer, as the value of the ratio v/G_0 decreases, due to an increase in the value of G_0. Note that at the V/I
35   boundary a transition occurs from vacancy dominated material to self-interstitial dominated material.

9

FIG. 6 is a top plan view of a single crystal silicon ingot or wafer showing regions of vacancy, V, and self-interstitial, I, dominated materials respectively, as well as the V/I boundary that exists between them.

FIG. 7a is a graph which shows an example of how the initial concentration of vacancies or self-interstitials changes as a function of radial position due to radial diffusion of self-interstitials. Also shown is how such diffusion causes the location of the V/I boundary to move closer to the center of the ingot (as a result of the recombination of vacancies and self-interstitials), as well as the concentration of self-interstitials, [I], to be suppressed.

FIG. 7b is a graph of ΔG_I as a function of radial position which shows an example of how the suppression of self-interstitial concentration, [I], (as depicted in FIG. 7a) is sufficient to maintain ΔG_I everywhere to a value which is less than the critical value at which the silicon self-interstitial reaction occurs.

FIG. 7c is a graph which shows another example of how the initial concentration of vacancies or self-interstitials changes as a function of radial position due to radial diffusion of self-interstitials. Note that, in comparison to FIG. 7a, such diffusion caused the location of the V/I boundary to be closer to the center of the ingot (as a result of the recombination of vacancies and self-interstitials), resulting in an increase in the concentration of interstitials in the region outside of the V/I boundary.

FIG. 7d is a graph of ΔG_I as a function of radial position which shows an example of how the suppression of self-interstitial concentration, [I], (as depicted in FIG. 7c) is not sufficient to maintain ΔG_I everywhere to a value which is less than the critical value at which the silicon self-interstitial reaction occurs.

FIG. 7e is a graph which shows another example of how the initial concentration of vacancies or self-interstitials changes as a function of radial position due to radial diffusion of self-interstitials. Note

5   that, in comparison to FIG. 7a, increased diffusion resulted in greater suppression the self-interstitial concentration.

FIG. 7f is a graph of ΔG_I as a function of radial position which shows an example of how greater

10 suppression of the self-interstitial concentration, [I], (as depicted in FIG. 7e) results in a greater degree of suppression in ΔG_I, as compared to FIG. 7b.

FIG. 7g is a graph which shows another example of how the initial concentration of vacancies or self-

15 interstitials changes as a function of radial position due to radial diffusion of self-interstitials. Note that, in comparison to FIG. 7c, increased diffusion resulted in greater suppression the self-interstitial concentration.

20 FIG. 7h is a graph of ΔG_I as a function of radial position which shows an example of how greater suppression of the self-interstitial concentration, [I], (as depicted in FIG. 7g) results in a greater degree of suppression in ΔG_I, as compared to FIG. 7d.

25 FIG. 7i is a graph which shows another example of how the initial concentration of vacancies or self-interstitials changes as a function of radial position due to radial diffusion of self-interstitials. Note that in this example a sufficient quantity of self-

30 interstitials recombine with vacancies, such that there is no longer a vacancy-dominated region.

FIG. 7j is a graph of ΔG_I as a function of radial position which shows an example of how radial diffusion of self-interstitials (as depicted in FIG. 7i) is

35 sufficient to maintain a suppression of agglomerated interstitial defects everywhere along the crystal radius.

FIG. 8 is a longitudinal, cross-sectional view of a single crystal silicon ingot showing, in detail, an axially symmetric region of a constant diameter portion of the ingot.

FIG. 9 is a longitudinal, cross-sectional view of a segment of a constant diameter portion of a single crystal silicon ingot, showing in detail axial variations in the width of an axially symmetric region.

FIG. 10 is a longitudinal, cross-sectional view of a segment of a constant diameter portion of a single crystal silicon ingot having axially symmetric region of a width which is less than the radius of the ingot, showing in detail that this region further contains a generally cylindrical region of vacancy dominated material.

FIG. 11 is a latitudinal, cross-sectional view of the axially symmetric region depicted in FIG. 10.

FIG. 12 is a longitudinal, cross-sectional view of a segment of a constant diameter portion of a single crystal silicon ingot having an axially symmetric region of a width which is equal to the radius of the ingot, showing in detail that this region is a generally cylindrical region of self-interstitial dominated material which is substantially free of agglomerated intrinsic point defects.

FIG. 13 is an image produced by a scan of the minority carrier lifetime of an axial cut of the ingot following a series of oxygen precipitation heat treatments, showing in detail a generally cylindrical region of vacancy dominated material, a generally annular shaped axially symmetric region of self-interstitial dominated material, the V/I boundary present between them, and a region of agglomerated interstitial defects.

FIG. 14 is a graph of pull rate (i.e. seed lift) as a function of crystal length, showing how the pull rate

12

is decreased linearly over a portion of the length of the
crystal.

FIG. 15 is an image produced by a scan of the
minority carrier lifetime of an axial cut of the ingot
following a series of oxygen precipitation heat
treatments, as described in Example 1.

FIG. 16 is a graph of pull rate as a function of
crystal length for each of four single crystal silicon
ingots, labeled 1-4 respectively, which are used to yield
a curve, labeled $v^*(Z)$, as described in Example 1.

FIG. 17 is a graph of the axial temperature gradient
at the crystal/melt interface, G_0, as a function of radial
position, for two different cases as described in Example
2.

FIG. 18 is a graph of the initial concentration of
vacancies, [V], or self-interstitials, [I], as a function
of radial position, for two different cases as described
Example 2.

FIG. 19 is a graph of temperature as a function of
axial position, showing the axial temperature profile in
ingots for two different cases as described in Example 3.

FIG. 20 is a graph of the self-interstitial
concentrations resulting from the two cooling conditions
illustrated in Fig. 19 and as more fully described in
Example 3.

FIG. 21 is an image produced by a scan of the
minority carrier lifetime of an axial cut of an entire
ingot following a series of oxygen precipitation heat
treatments, as described in Example 4.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As used herein, the following phrases or terms shall
have the given meanings: "agglomerated intrinsic point
defects" mean defects caused (i) by the reaction in which
vacancies agglomerate to produce D-defects, flow pattern
defects, gate oxide integrity defects, crystal originated

13

particle defects, crystal originated light point defects,
and other such vacancy related defects, or (ii) by the
reaction in which self-interstitials agglomerate to
produce dislocation loops and networks, and other such
5   self-interstitial related defects; "agglomerated
interstitial defects" shall mean agglomerated intrinsic
point defects caused by the reaction in which silicon
self-interstitial atoms agglomerate; "agglomerated
vacancy defects" shall mean agglomerated vacancy point
10   defects caused by the reaction in which crystal lattice
vacancies agglomerate; "radius" means the distance
measured from a central axis to a circumferential edge of
a wafer or ingot; "substantially free of agglomerated
intrinsic point defects" shall mean a concentration of
15   agglomerated defects which is less than the detection
limit of these defects, which is currently about 10^4
defects/cm^3; "V/I boundary" means the position along the
radius of an ingot or wafer at which the material changes
from vacancy dominated to self-interstitial dominated;
20   and "vacancy dominated" and "self-interstitial dominated"
mean material in which the intrinsic point defects are
predominantly vacancies or self-interstitials,
respectively.

In accordance with the present invention, it has
25   been discovered that the reaction in which silicon self-
interstitial atoms react to produce agglomerated
interstitial defects can be suppressed during the growth
of single crystal silicon ingots. Without being bound to
any particular theory, it is believed that the
30   concentration of self-interstitials is controlled during
the growth and cooling of the crystal ingot in the
process of the present invention, such that the change in
free energy of the system never exceeds a critical value
at which the agglomeration reaction spontaneously occurs
35   to produce agglomerated interstitial defects.

14

In general, the change in system free energy available to drive the reaction in which agglomerated interstitial defects are formed from silicon self-interstitials in single crystal silicon is governed by
5   Equation (I):

$$\Delta G_I = kT \ln\left(\frac{[I]}{[I]^{eq}}\right) \quad (I)$$

wherein
10   ΔG_I is the change in free energy,
             k is the Boltzmann constant,
             T is the temperature in K,
             [I] is the concentration of self-interstitials at a point in space and time in the single crystal
15   silicon, and
             $[I]^{eq}$ is the equilibrium concentration of self-interstitials at the same point in space and time at which [I] occurs and at the temperature, T.

According to this equation, for a given concentration of
20   self-interstitials, [I], a decrease in the temperature, T, generally results in an increase in ΔG_I due to a sharp decrease in $[I]^{eq}$ with temperature.
             Fig. 2 schematically illustrates the change in ΔG_I and the concentration of silicon self-interstitials for
25   an ingot which is cooled from the temperature of solidification without simultaneously employing some means for suppression of the concentration of silicon self-interstitials. As the ingot cools, ΔG_I increases according to Equation (I), due to the increasing
30   supersaturation of [I], and the energy barrier for the formation of agglomerated interstitial defects is approached. As cooling continues, this energy barrier is eventually exceeded, at which point a reaction occurs. This reaction results in the formation of agglomerated

15

interstitial defects and the concomitant decrease in ΔG_I as the supersaturated system is relaxed.

The agglomeration of self-interstitials can be avoided as the ingot cools from the temperature of solidification by maintaining the free energy of the silicon self-interstitial system at a value which is less than that at which an agglomeration reaction will occur. In other words, the system can be controlled so as to never become critically supersaturated. This can be achieved by establishing an initial concentration of self-interstitials which is sufficiently low such that critical supersaturation is never achieved. However, in practice such concentrations are difficult to achieve across an entire crystal radius and, in general, therefore, critical supersaturation may be avoided by suppressing the initial silicon self-interstitial concentration subsequent to crystal solidification.

Figs. 3 and 4 schematically illustrate two possible effects of suppressing [I] upon the increase in ΔG_I as the ingot of Fig. 2 is cooled from the temperature of solidification. In Fig. 3, the suppression of [I] results in a decrease in the rate of increase of ΔG_I, but in this case, the suppression is insufficient to maintain ΔG_I everywhere at a value which is less than the critical value at which the reaction occurs; as a result, the suppression merely serves to reduce the temperature at which the reaction occurs. In Fig. 4, an increased suppression of [I] is sufficient to maintain ΔG_I everywhere to a value which is less than the critical value at which the reaction occurs; the suppression, therefore, inhibits the formation of defects.

Surprisingly, it has been found that due to the relatively large mobility of self-interstitials, it is possible to effect the suppression over relatively large distances by the radial diffusion of self-interstitials to sinks located at the crystal surface or to vacancy

16

dominated regions. Radial diffusion can be effectively
used to suppress the concentration of self-interstitials,
provided sufficient time is allowed for the radial
diffusion of the initial concentration of self-
interstitials. In general, the diffusion time will
depend upon the radial variation in the initial
concentration of self-interstitials, with lesser radial
variations requiring shorter diffusion times.

Typically, the axial temperature gradient, G_0,
increases as a function of increasing radius for single
crystal silicon which is grown according to the
Czochralski method. This means that the value of v/G_0 is
typically not singular across the radius of an ingot. As
a result of this variation, the type and initial
concentration of intrinsic point defects is not constant.
If the critical value of v/G_0, denoted in Figs. 5 and 6 as
the V/I boundary 2, is reached at some point along the
radius 4, the material will switch from being vacancy
dominated to self-interstitial dominated. In addition,
the ingot will contain an axially symmetric region of
self-interstitial dominated material 6 (in which the
initial concentration of silicon self-interstitial atoms
increases as a function of increasing radius),
surrounding a generally cylindrical region of vacancy
dominated material 8 (in which the initial concentration
of vacancies decreases as a function of increasing
radius).

Figs. 7a and 7b schematically illustrate the effect
of suppressing [I] upon the increase in ΔG_I as an ingot is
cooled from the temperature of solidification in
accordance with one embodiment of the present invention.
When the ingot is pulled in accordance with the
Czochralski method, the ingot contains an axially
symmetric region of interstitial dominated material
extending from the edge of the ingot to the position
along the radius at which the V/I boundary occurs and a

17

generally cylindrical region of vacancy dominated
material extending from the center of the ingot to the
position along the radius at which the V/I boundary
occurs. As the ingot is cooled from the temperature of
5   solidification, radial diffusion of interstitial atoms
causes a radially inward shift in the V/I boundary due to
a recombination of self-interstitials with vacancies and
a significant suppression of the self-interstitial
concentration outside the V/I boundary. Furthermore, the
10   suppression of [I] is sufficient to maintain ΔG_I
everywhere to a value which is less than the critical
value at which the silicon self-interstitial reaction
occurs.

        Referring now to Figs. 8 and 9, in the process of
15   the present invention a single crystal silicon ingot 10
is grown in accordance with the Czochralski method. The
silicon ingot comprises a central axis 12, a seed-cone
14, an end-cone 16 and a constant diameter portion 18
between the seed-cone and the end-cone. The constant
20   diameter portion has a circumferential edge 20 and a
radius 4 extending from the central axis to the
circumferential edge. The process comprises controlling
the growth velocity, v, and the instantaneous axial
temperature gradient, G_0, of the crystal during the growth
25   of the constant diameter portion of the ingot to cause
the formation of an axially symmetric region 6 which,
upon cooling the ingot from the solidification
temperature, is substantially free of agglomerated
intrinsic point defects.

30   The growth conditions are preferably controlled to
maintain the V/I boundary 2 at a position which maximizes
the volume of the axially symmetric region 6 relative to
the volume of the constant diameter portion 18 of the
ingot 10. In general, therefore, it is preferred that
35   the axially symmetric region have a width 22 (as measured
from the circumferential edge radially toward the central

18

axis of the ingot) and a length 24 (as measured along the
central axis of the ingot) which equals the radius 4 and
length 26, respectively of the constant diameter portion
of the ingot. As a practical matter, however, operating
5   conditions and crystal puller hardware constraints may
dictate that the axially symmetric region occupy a lesser
proportion of the constant diameter portion of the ingot.
In general, therefore, the axially symmetric region
preferably has a width of at least about 30%, more
10   preferably at least about 40%, still more preferably at
least about 60%, and most preferably at least about 80%
of the radius of the constant diameter portion of the
ingot. In addition, the axially symmetric region extends
over a length of at least about 20%, preferably at least
15   about 40%, more preferably at least about 60%, and still
more preferably at least about 80% of the length of the
constant diameter portion of the ingot.

Referring to Fig. 9, the width 22 of the axially
symmetric region 6 may have some variation along the
20   length of the central axis 12. For an axially symmetric
region of a given length, therefore, the width is
determined by measuring the distance from the
circumferential edge 20 of the ingot 10 radially toward a
point which is farthest from the central axis. In other
25   words, the width 22 is measured such that the minimum
distance within the given length 24 of the axially
symmetric region 6 is determined.

Referring now to Figs. 10 and 11, when the axially
symmetric region 6 of the constant diameter portion 18 of
30   the ingot 10 has a width 22 which is less than the radius
4 of the constant diameter portion, the region is
generally annular in shape. A generally cylindrical
region of vacancy dominated material 8, which is centered
about the central axis 12, is located radially inward of
35   the generally annular shaped segment. Referring to
Figure 12, it is to be understood that when the width 22

19

of the axially symmetric region 6 is equal to the radius
4 of the constant diameter portion 18, the region does
not contain this vacancy dominated region; rather, the
axially symmetric region itself is generally cylindrical
5   and contains self-interstitial dominated material which
is substantially free of agglomerated intrinsic point
defects.

While it is generally preferred that the crystal
growth conditions be controlled to maximize the width of
10   the interstitial dominated region, there may be limits
for a given crystal puller hot zone design. As the V/I
boundary is moved closer to the central crystal axis,
provided the cooling conditions and $G_0(r)$ do not change,
where $G_0(r)$ is the radial variation of G_0, the minimum
15   amount of radial diffusion required increases. In these
circumstances, there may be a minimum radius of the
vacancy dominated region which is required to suppress
the formation of agglomerated interstitial defects by
radial diffusion.
20   Figs. 7c and 7d schematically illustrate an example
in which the minimum radius of the vacancy dominated
region is exceeded. In this example, the cooling
conditions and $G_0(r)$ are the same as those employed for
the crystal of Figs. 7a and 7b in which there was
25   sufficient outdiffusion to avoid agglomerated
interstitial defects for the position of the V/I boundary
illustrated. In Figs. 7c and 7d, the position of the V/I
boundary is moved closer to the central axis (relative to
Figs. 7a and 7b) resulting in an increase in the
30   concentration of interstitials in the region outside of
the V/I boundary. As a result, more radial diffusion is
required to sufficiently suppress the interstitial
concentration. If sufficient outdiffusion is not
achieved, the system ΔG_I will increase beyond the critical
35   value and the reaction which produces agglomerated
interstitial defects will occur, producing a region of

20

these defects in an annular region between the V/I
boundary and the edge of the crystal. The radius of the
V/I boundary at which this occurs is the minimum radius
for the given hot zone. This minimum radius is decreased
5   if more radial diffusion of interstitials is allowed.

        Figs. 7e, 7f, 7g and 7h illustrate the effect of an
increased radial outdiffusion on interstitial
concentration profiles and the rise of system ΔG_I for a
crystal grown with the same initial vacancy and
10   interstitial concentration profiles as the crystal
exemplified in Figs. 7a, 7b, 7c and 7d. Increased radial
diffusion of interstitials results in a greater
suppression of interstitial concentration, thus
suppressing the rise in the system ΔG_I to a greater degree
15   than in Figs. 7a, 7b, 7c and 7d. In this case the system
ΔG_I is not exceeded for the smaller radius of the V/I
boundary.

        Figs. 7i and 7j illustrate an example in which
sufficient radial diffusion is allowed such that the
20   minimum radius is reduced to zero by insuring sufficient
radial diffusion to achieve a suppression of agglomerated
interstitial defects everywhere along the crystal radius.

        In a preferred embodiment of the process of the
present invention, the initial concentration of silicon
25   self-interstitial atoms is controlled in the axially
symmetric, self-interstitial dominated region of the
ingot. Referring again to Fig. 1, in general, the
initial concentration of silicon self-interstitial atoms
is controlled by controlling the crystal growth velocity,
30   v, and the instantaneous axial temperature gradient, G_0,
such that the value of the ratio v/G_0 is relatively near
the critical value of this ratio, at which the V/I
boundary occurs. In addition, the instantaneous axial
temperature gradient, G_0, can be established such that the
35   variation of G_0 (and thus, v/G_0) as a function of the
ingot radius is also controlled.

21

The growth velocity, v, and the instantaneous axial temperature gradient, G_0, are typically controlled such that the ratio v/G_0 ranges in value from about 0.5 to about 2.5 times the critical value of v/G_0 (i.e., about
5   1×10^{-5} cm^2/sK to about 5×10^{-5} cm^2/sK based upon currently available information for the critical value of v/G_0). Preferably, the ratio v/G_0 will range in value from about 0.6 to about 1.5 times the critical value of v/G_0 (i.e., about 1.3×10^{-5} cm^2/sK to about 3×10^{-5} cm^2/sK based upon
10   currently available information for the critical value of v/G_0). Most preferably, the ratio v/G_0 will range in value from about 0.75 to about 1 times the critical value of v/G_0 (i.e., about 1.6×10^{-5} cm^2/sK to about 2.1×10^{-5} cm^2/sK based upon currently available information
15   for the critical value of v/G_0). These ratios are achieved by independent control of the growth velocity, v, and the instantaneous axial temperature gradient, G_0.

In general, control of the instantaneous axial temperature gradient, G_0, may be achieved primarily
20   through the design of the "hot zone" of the crystal puller, i.e. the graphite (or other materials) that makes up the heater, insulation, and heat shields, among other things. Although the design particulars may vary depending upon the make and model of the crystal puller,
25   in general, G_0 may be controlled using any of the means currently known in the art for minimizing axial variations in heat transfer at the melt/solid interface, including reflectors, radiation shields, purge tubes, light pipes, and heaters. In general, radial variations
30   in G_0 are minimized by positioning such an apparatus within about one crystal diameter above the melt/solid interface. G_0 can be controlled further by adjusting the position of the apparatus relative to the melt and crystal. This is accomplished either by adjusting the
35   position of the apparatus in the hot zone, or by adjusting the position of the melt surface in the hot

22

zone. Either, or both, of these methods can be used
during a batch Czochralski process in which melt volume
is depleted during the process.

It is generally preferred for some embodiments of
the present invention that the instantaneous axial
temperature gradient, G_0, be relatively constant as a
function of diameter of the ingot. However, it should be
noted that as improvements in hot zone design allow for
variations in G_0 to be minimized, mechanical issues
associated with maintaining a constant growth rate become
an increasingly important factor. This is because the
growth process becomes much more sensitive to any
variation in the pull rate, which in turn directly
effects the growth rate, v. In terms of process control,
this means that it is favorable to have values for G_0
which differ over the radius of the ingot. Significant
differences in the value of G_0, however, can result in a
large concentration of self-interstitials near the wafer
edge and, thereby, increase the difficultly in avoiding
the formation of agglomerated intrinsic point defects.

In view of the foregoing, the control of G_0 involves
a balance between minimizing radial variations in G_0 and
maintaining favorable process control conditions.
Typically, therefore, the pull rate after about one
diameter of the crystal length will range from about 0.2
mm/minute to about 0.8 mm/minute. Preferably, the pull
rate will range from about 0.25 mm/minute to about 0.6
mm/minute and, most preferably, from about 0.3 mm/minute
to about 0.5 mm/minute. It is to be noted the stated
ranges are typical for 200 mm diameter crystals.
However, the pull rate is dependent upon both the crystal
diameter and crystal puller design. In general, the pull
rate will decrease as the crystal diameter increases.

The amount of self-interstitial diffusion may be
controlled by controlling the cooling rate as the ingot
is cooled from the solidification temperature (about

23

1410°C) to the temperature at which silicon self-
interstitials become immobile, for commercially practical
purposes. Silicon self-interstitials appear to be
extremely mobile at temperatures near the solidification

5   temperature of silicon, i.e. about 1410°C. This
mobility, however, decreases as the temperature of the
single crystal silicon ingot decreases. Experimental
evidence obtained to-date suggests that the diffusion
rate of self-interstitials slows such a considerable

10   degree that they are essentially immobile for
commercially practical time periods at temperatures less
than about 700°C, and perhaps at temperatures as great as
800°C, 900°C, or even 1,000°C.

Within the range of temperatures at which self-

15   interstitials appear to be mobile, and depending upon the
temperature in the hot zone, the cooling rate will
typically range from about 0.2 °C/minute to about
2 °C/minute. Preferably, the cooling rate will range
from about 0.2 °C/minute to about 1.5 °C/minute and, more

20   preferably, from about 0.2 °C/minute to about
1 °C/minute. Control of the cooling rate can be achieved
by using any means currently known in the art for
minimizing heat transfer, including the use of
insulators, heaters, and radiation shields.

25   As previously noted, a minimum radius of the vacancy
dominated region exists for which the suppression of
agglomerated interstitial defects may be achieved. The
value of the minimum radius depends on $v/G_0(r)$ and the
cooling rate. As crystal puller and hot zone designs

30   will vary, the ranges presented above for $v/G_0(r)$, pull
rate, and cooling rate will also vary. Likewise these
conditions may vary along the length of a growing
crystal. Also as noted above, the width of the
interstitial dominated region free of agglomerated

35   interstitial defects is preferably maximized. Thus, it
is desirable to maintain the width of this region to a

24

value which is as close as possible to, without
exceeding, the difference between the crystal radius and
the minimum radius of the vacancy dominated region along
the length of the growing crystal in a given crystal
5   puller.

The optimum width of the axially symmetric region
and the required optimal crystal pulling rate profile for
a given crystal puller hot zone design may be determined
empirically. Generally speaking, this empirical approach
10 involves first obtaining readily available data on the
axial temperature profile for an ingot grown in a
particular crystal puller, as well as the radial
variations in the instantaneous axial temperature
gradient for an ingot grown in the same puller.
15 Collectively, this data is used to pull one or more
single crystal silicon ingots, which are then analyzed
for the presence of agglomerated interstitial defects.
In this way, an optimum pull rate profile can be
determined.

20   Fig. 13 is an image produced by a scan of the
minority carrier lifetime of an axial cut of a section of
a 200 mm diameter ingot following a series of oxygen
precipitation heat-treatments which reveal defect
distribution patterns. It depicts an example in which a
25 near-optimum pull rate profile is employed for a given
crystal puller hot zone design. In this example, a
transition occurs from the optimum $v/G_0(r)$ at which the
axially symmetric region has the maximum width, to a
$v/G_0(r)$ in which the maximum width of the interstitial
30 dominated region is exceeded, resulting in the generation
of regions of agglomerated interstitial defects 28.

In addition to the radial variations in v/G_0
resulting from an increase in G_0 over the radius of the
ingot, v/G_0 may also vary axially as a result of a change
35 in v, or as a result of natural variations in G_0 due to
the Czochralski process. For a standard Czochralski

25

process, v is altered as the pull rate is adjusted
throughout the growth cycle, in order to maintain the
ingot at a constant diameter. These adjustments, or
changes, in the pull rate in turn cause v/G_0 to vary over
5   the length of the constant diameter portion of the ingot.
In accordance with the process of the present invention,
the pull rate is therefore controlled in order to
maximize the width of the axially symmetric region of the
ingot. As a result, however, variations in the radius of
10   the ingot may occur. In order to ensure that the
resulting ingot has a constant diameter, the ingot is
therefore preferably grown to a diameter larger than that
which is desired. The ingot is then subjected to
processes standard in the art to remove excess material
15   from the surface, thus ensuring that an ingot having a
constant diameter portion is obtained.

       For an ingot prepared in accordance with the process
of the present invention and having a V/I boundary,
experience has shown that low oxygen content material,
20   i.e., less than about 13 PPMA (parts per million atomic,
ASTM standard F-121-83), is preferred. More preferably,
the single crystal silicon contains less than about 12
PPMA oxygen, still more preferably less than about 11
PPMA oxygen, and most preferably less than about 10 PPMA
25   oxygen. This is because, in medium to high oxygen
contents wafers, i.e., 14 PPMA to 18 PPMA, the formation
of oxygen-induced stacking faults and bands of enhanced
oxygen clustering just inside the V/I boundary becomes
more pronounced. Each of these are a potential source
30   for problems in a given integrated circuit fabrication
process.

       The effects of enhanced oxygen clustering may be
further reduced by two methods, used singularly or in
combination. Oxygen precipitate nucleation centers
35   typically form in silicon which is annealed at a
temperature in the range of about 350° to about 750 °C.

26

For some applications, therefore, it may be preferred
that the crystal be a "short" crystal, that is, a crystal
which has been grown in a Czochralski process until the
seed end has cooled from the melting point of silicon
5   (1410° C) to about 750° C after which the ingot is
rapidly cooled. In this way, the time spent in the
temperature range critical for nucleation center
formation is kept to a minimum and the oxygen precipitate
nucleation centers have inadequate time to form in the
10   crystal puller.
     Alternatively, and more preferably, oxygen
precipitate nucleation centers formed during the growth
of the single crystal are dissolved by annealing the
single crystal silicon. Provided they have not been
15   subjected to a stabilizing heat-treatment, oxygen
precipitate nucleation centers can be annealed out of
silicon by rapidly heating the silicon to a temperature
of at least about 875° C and preferably continuing to
increase the temperature to at least 1000° C. By the
20   time the silicon reaches 1000° C, substantially all
(e.g., >99%) of such defects have annealed out. It is
important that the wafers be rapidly heated to these
temperatures, i.e., that the rate of temperature increase
be at least about 10° C per minute and more preferably at
25   least about 50° C per minute. Otherwise, some or all of
the oxygen precipitate nucleation centers may be
stabilized by the heat-treatment. Equilibrium appears to
be reached in relatively short periods of time, i.e., on
the order of 1 minute. Accordingly, oxygen precipitate
30   nucleation centers in the single crystal silicon may be
dissolved by annealing it at a temperature of at least
about 875° C for a period of at least about 30 seconds,
preferably at least about 10 minutes. The dissolution
may be carried out in a conventional furnace or in a
35   rapid thermal annealing (RTA) system. In addition, the

27

dissolution may carried out on crystal ingots or on wafers, preferably wafers.

Although the temperature at which a self-interstitial agglomeration reaction occurs may in theory
5   vary over a wide range of temperatures, as a practical matter this range appears to be relatively narrow for conventional, Czochralski grown silicon. This is a consequence of the relatively narrow range of initial self-interstitial concentrations which are typically
10   obtained in silicon grown according to the Czochralski method. In general, therefore, a self-interstitial agglomeration reaction will typically occur, if at all, at temperatures within the range of about 1100°C to about 800°C.

15   As the Examples given below illustrate, the present invention affords a process for preparing a single crystal silicon ingot in which, as the ingot cools from the solidification temperature in accordance with the Czochralski method, the agglomeration of intrinsic point
20   defects is prevented within an axially symmetric region of the constant diameter portion of the ingot, from which wafers may be sliced.

The following Examples set forth one set of conditions that may be used to achieve the desired
25   result. Alternative approaches exist for determining an optimum pull rate profile for a given crystal puller. For example, rather than growing a series of ingots at various pull rates, a single crystal could be grown at pull rates which increase and decrease along the length
30   of the crystal; in this approach, agglomerated self-interstitial defects would be caused to appear and disappear multiple times during growth of a single crystal. Optimal pull rates could then be determined for a number of different crystal positions. Accordingly,
35   the following Examples should not be interpreted in a limiting sense.

28

Example 1
Optimization Procedure For A Crystal
Puller Having A Pre-existing Hot Zone Design

A first 200 mm single crystal silicon ingot was
5   grown under conditions in which the pull rate was ramped
linearly from 0.75 mm/min. to 0.35 mm/min. over the
length of the crystal. Fig. 14 shows the pull rate as a
function of crystal length. Taking into account the pre-
established axial temperature profile of a growing 200 mm
10 ingot in the crystal puller and the pre-established
radial variations in the instantaneous axial temperature
gradient, G_0, i.e., the axial temperature gradient at the
melt/solid interface, these pull rates were selected to
insure that ingot would be vacancy dominated material
15 from the center to the edge at one end of the ingot and
interstitial dominated material from the center to the
edge of the other end of the ingot. The grown ingot was
sliced longitudinally and analyzed to determine where the
formation of agglomerated interstitial defects begins.
20   Fig. 15 is an image produced by a scan of the
minority carrier lifetime of an axial cut of the ingot
over a section ranging from about 635 mm to about 760 mm
from the shoulder of the ingot following a series of
oxygen precipitation heat-treatments which reveal defect
25 distribution patterns. At a crystal position of about
680 mm, a band of agglomerated interstitial defects 28
can be seen. This position corresponds to a critical
pull rate of $v^*(680 \text{ mm}) = 0.33$ mm/min. At this point, the
width of the axially symmetric region 6 (a region which
30 is interstitial dominated material but which lacks
agglomerated interstitial defects) is at its maximum; the
width of the vacancy dominated region 8, $R_v^*(680)$ is about
35 mm and the width of the axially symmetric region,
$R_I^*(680)$ is about 65 mm.
35   A series of four single crystal silicon ingots were
then grown at steady state pull rates which were somewhat

29

greater than and somewhat less than the pull rate at
which the maximum width of the axially symmetric region
of the first 200 mm ingot was obtained. Fig. 16 shows
the pull rate as a function of crystal length for each of
5   the four crystals, labeled, respectively, as 1-4. These
four crystals were then analyzed to determine the axial
position (and corresponding pull rate) at which
agglomerated interstitial defects first appear or
disappear. These four empirically determined points
10   (marked "*") are shown in Fig. 16. Interpolation between
and extrapolation from these points yielded a curve,
labeled $v^*(Z)$ in Fig. 16. This curve represents, to a
first approximation, the pull rate for 200 mm crystals as
a function of length in the crystal puller at which the
15   axially symmetric region is at its maximum width.

         Growth of additional crystals at other pull rates
and further analysis of these crystals would further
refine the empirical definition of $v^*(Z)$.

                         Example 2
20   Reduction of Radial Variation in $G_0(r)$
         Figs. 17 and 18 illustrate the improvement in
quality that can be achieved by reduction of the radial
variation in the axial temperature gradient at the
crystal/melt interface, $G_0(r)$. The initial concentration
25   (about 1 cm from the crystal/melt interface) of vacancies
and interstitials are calculated for two cases with
different $G_0(r)$: (1) $G_0(r) = 2.65 + 5 \times 10^{-4} r^2$ (K/mm) and (2)
$G_0(r) = 2.65 + 5 \times 10^{-5} r^2$ (K/mm). For each case the pull
rate was adjusted such that the boundary between vacancy-
30   rich silicon and interstitial-rich silicon is at a radius
of 3 cm. The pull rate used for case 1 and 2 were 0.4
and 0.35 mm/min, respectively. From Fig. 18 it is clear
that the initial concentration of interstitials in the
interstitial-rich portion of the crystal is dramatically
35   reduced as the radial variation in the initial axial

30

temperature gradient is reduced. This leads to an
improvement in the quality of the material since it
becomes easier to avoid the formation of interstitial
defect clusters due to supersaturation of interstitials.

Example 3

Increased Out-diffusion Time for Interstitials

Figs. 19 and 20 illustrate the improvement in
quality that can be achieved by increasing the time for
out-diffusion of interstitials. The concentration of
interstitials is calculated for two cases with differing
axial temperature profiles in the crystal, dT/dz. The
axial temperature gradient at the crystal/melt interface
is the same for both cases, so that the initial
concentration (about 1 cm from the crystal/melt
interface) of interstitials is the same for both cases.
In this example, the pull rate was adjusted such that the
entire crystal is interstitial-rich. The pull rate was
the same for both cases, 0.32 mm/min. The longer time
for interstitial out-diffusion in case 2 results in an
overall reduction of the interstitial concentration.
This leads to an improvement in the quality of the
material since it becomes easier to avoid the formation
of interstitial defect clusters due to supersaturation of
interstitials.

Example 4

A 700 mm long, 150 mm diameter crystal was grown
with a varying pull rate. The pull rate varied nearly
linearly from 1.2 mm/min at the shoulder to 0.4 mm/min at
430 mm from the shoulder, and then nearly linearly back
to 0.65 mm/min at 700 mm from the shoulder. Under these
conditions in this particular crystal puller, the entire
radius is grown under interstitial-rich conditions over
the length of crystal about 320 mm to about 525 mm from
the shoulder of the crystal. At an axial position of

31

about 525 mm and a pull rate of about 0.47 mm/min, the crystal is free of agglomerated intrinsic point defects clusters across the entire diameter. Stated another way, there is one small section of the crystal in which the
5   width of the axially symmetric region, i.e., the region which is substantially free of agglomerated defects, is equal to the radius of the ingot.

In view of the above, it will be seen that the several objects of the invention are achieved.
10   As various changes could be made in the above compositions and processes without departing from the scope of the invention, it is intended that all matter contained in the above description be interpreted as illustrative and not in a limiting sense.

32

What is claimed is:

1.   A single crystal silicon wafer having a central
axis, a front side and a back side which are generally
perpendicular to the axis, a circumferential edge, and a
radius extending from the central axis to the
5   circumferential edge of the wafer, the wafer comprising
an axially symmetric region which is substantially
free of agglomerated intrinsic point defects, the axially
symmetric region extending radially inwardly from the
circumferential edge of the wafer and having a width, as
10   measured from the circumferential edge radially toward
the center axis, which is at least about 40% the length
of the radius of the wafer.

2.   The wafer as set forth in claim 1 wherein the
axially symmetric region is generally annular in shape
and the wafer additionally comprises a generally
cylindrical region consisting of vacancy dominated
5   material which is radially inward of the annular region.

3.   The wafer as set forth in claim 1 wherein the
wafer has as oxygen content which is less than about 13
PPMA.

4.   The wafer as set forth in claim 1 wherein the
wafer has as oxygen content which is less than about 11
PPMA.

5.   The wafer as set forth in claim 1 wherein the
wafer has an absence of oxygen precipitate nucleation
centers.

6.   A single crystal silicon ingot having a central
axis, a seed-cone, an end-cone, and a constant diameter
portion between the seed-cone and the end-cone having a
circumferential edge and a radius extending from the

33

5   central axis to the circumferential edge, the single crystal silicon ingot being characterized in that after the ingot is grown and cooled from the solidification temperature, the constant diameter portion contains an axially symmetric region which is substantially free of
10   agglomerated intrinsic point defects wherein the axially symmetric region extends radially inwardly from a circumferential edge of the ingot, has a width as measured from the circumferential edge radially toward the central axis of the ingot which is at least about 30%
15   the length of the radius of the constant diameter portion, and has a length as measured along the central axis of at least about 20% the length of the constant diameter portion of the ingot.

7.   The single crystal silicon ingot as set forth in claim 6 wherein the length of the axially symmetric region is at least 40% the length of the constant diameter portion of the ingot.

8.   The single crystal silicon ingot as set forth in claim 7 wherein the length of the axially symmetric region is at least 60% the length of the constant diameter portion of the ingot.

9.   The single crystal silicon ingot as set forth in claim 6 wherein the axially symmetric region has a width which is at least about 60% the length of the radius of the constant diameter portion.

10.   The single crystal silicon ingot as set forth in claim 9 wherein the axially symmetric region has a width which is at least about 80% the length of the radius of the constant diameter portion.

34

11. A process for growing a single crystal silicon ingot in which the ingot comprises a central axis, a seed-cone, an end-cone and a constant diameter portion between the seed-cone and the end-cone having a
5   circumferential edge and a radius extending from the central axis to the circumferential edge, the ingot being grown from a silicon melt and then cooled from the solidification temperature in accordance with the Czochralski method, the process comprising
10   controlling a growth velocity, v, and an instantaneous axial temperature gradient, G_0, of the crystal during the growth of the constant diameter portion of the ingot to cause the formation of an axially symmetrical segment which, upon cooling of the ingot from
15   the solidification temperature, is substantially free of agglomerated intrinsic point defects wherein the axially symmetric region extends inwardly from the circumferential edge of the ingot, has a width as measured from the circumferential edge radially toward
20   the central axis of the ingot which is at least about 30% the length of the radius of the ingot, and has a length as measured along the central axis of at least about 20% the length of the constant diameter portion of the ingot.

12. The process as set forth in claim 11 wherein the length of the axially symmetric region is at least 40% the length of the constant diameter portion of the ingot.

13. The process as set forth in claim 12 wherein the length of the axially symmetric region is at least 60% the length of the constant diameter portion of the ingot.

14. The process as set forth in claim 11 wherein the axially symmetric region has a width which is at

35

least about 60% the length of the radius of the constant
diameter portion.

15. The process as set forth in claim 14 wherein
the axially symmetric region has a width which is at
least about 80% the length of the radius of the constant
diameter portion.

16. A process for growing a single crystal silicon
ingot, the single crystal silicon ingot being
characterized in that, after the ingot is grown from a
silicon melt and cooled from the solidification
5   temperature in accordance with the Czochralski method, a
constant diameter portion of the ingot contains an
axially symmetric region which is substantially free of
agglomerated intrinsic point defects, the process
comprising
10   controlling a growth velocity, v, and an
instantaneous axial temperature gradient, G_0, such that a
ratio v/G_0 ranges in value from about 0.6 to about 1.5
times the critical value of v/G_0.

17. A process for growing a single crystal silicon
ingot, the single crystal silicon ingot being
characterized in that, after the ingot is grown from a
silicon melt and cooled from the solidification
5   temperature in accordance with the Czochralski method, a
constant diameter portion of the ingot contains an
axially symmetric segment which is substantially free of
agglomerated intrinsic point defects, the process
comprising
10   controlling a growth velocity, v, and an
instantaneous axial temperature gradient, G_0, such that a
ratio v/G_0 ranges in value from about 0.6 to about 1.5
times the critical value of v/G_0; and

36

controlling a cooling rate within a temperature
15   range of about 1400 °C to about 800 °C, such that the
rate ranges from about 0.2 °C/minute to about
1.5 °C/minute.

18.   The process of claim 17 wherein the growth
velocity, v, and the instantaneous axial temperature
gradient, G_0, are controlled such that the ratio v/G_0
ranges in value from about 0.75 to about 1 times the
5   critical value of v/G_0.

19.   The process of claim 17 wherein the cooling
rate is controlled within a temperature range of about
1400 °C to about 1000 °C.

20.   The process of claim 19 wherein the cooling
rate is controlled such that the rate ranges from about
0.2°C/minute to about 1 °C/minute.

21.   The process of claim 17 wherein oxygen
precipitate nucleation centers formed during the growth
of the single crystal are dissolved by annealing the
single crystal silicon.

FIG. 1

FIG. 2

FIG. 3

FIG. 4

FIG. 5

FIG. 6

FIG.7A

FIG.7B

FIG.7C

FIG.7D

FIG.7E

FIG.7F

FIG.7G

MORE
RADIAL
DIFFUSION

CENTER   EDGE

RADIAL POSITION

FIG.7H

$\triangle G_I$

$\triangle G_I$ CRITICAL

NO AGGLOMERATED
INTERSTITAL DEFECTS

CENTER   EDGE

RADIAL POSITION

FIG.7I

FIG.7J

FIG. 8

SEED CONE, 14

10

AXIALLY SYMMETRIC
REGION, 6

CONSTANT
DIAMETER
PORTION, 18

WIDTH AS MEASURED FROM
EDGE TOWARD AXIS, 22

RADIUS, 4

CIRCUMFERENTIAL
EDGE, 20

26

END CONE, 16

AXIS, 12

FIG. 9

V/I BOUNDARY, 2
SHOWING VARIABILITY

LENGTH OF
REGION, 24

WIDTH OF AXIALLY SYMMETRIC
REGION WITHIN GIVEN LENGTH, 22

AXIS, 12

FIG.10

VACANCY
DOMINATED
MATERIAL, 8

AXIALLY SYMMETRIC
REGION, 6

WIDTH, 22
RADIUS, 4

AXIS, 12

FIG.11

RADIUS, 4

WIDTH OF AXIALLY
SYMMETRIC REGION, 22

VACANCY
DOMINATED
MATERIAL, 8

FIG.12

AXIALLY SYMMETRIC
REGION; SELF-INTERSTITIAL
DOMINATED, 6

LENGTH
OF REGION, 24

WIDTH, 22
RADIUS, 4

AXIS, 12

FIG.13

V/I BOUNDARY, 2

VACANCY DOMINATED, 8

AGGLOMERATED
INTERSTITIAL DEFECTS, 28

CIRCUMFERENTIAL
EDGE, 20

INTERSTITIAL
DOMINATED, 6

AXIS, 12

FIG.14

FIG. 15

AXIAL POSITION

VACANCY DOMINATED, 8

V/I BOUNDARY, 2

PULL RATE

INTERSTITIAL DOMINATED, 6

0.33 mm/min.

AGGLOMERATED INTERSTITIAL DEFECTS, 28

635 mm

680 mm

760 mm

FIG.16

FIG. 17

FIG. 18

FIG.19

FIG.20

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6   C30B15/00   C30B33/00   C30B29/06

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6   C30B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 97 26393 A (SHIN ETSU HANDOTAI) 24 July 1997 see abstract ---	1
X	DE 44 14 947 A (WACKER CHEMITRONIC GMBH) 31 August 1995 see column 3, line 31 - line 62 ---	11
X	AMMON ET AL: "The dependence of bulk defects on the axial temperature gradient of silicon crystals during Czochralski growth" JOURNAL OF CRYSTAL GROWTH., vol. 151, no. 3/4, 1 June 1995, AMSTERDAM NL, pages 273-277, XP000514096 see the whole document ---	11

−/−−

[X] Further documents are listed in the continuation of box C.   [X] Patent family members are listed in annex.

° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
5 August 1998	17/08/1998

Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Cook, S

Form PCT/ISA/210 (second sheet) (July 1992)

page 1 of 2

INTERNATIONAL SEARCH REPORT

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication,where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 474 020 A (BELL ET AL) 12 December 1995 see column 5, line 41 - line 52; figure 4B ---	1-6
A	GB 2 182 262 A (SONY CORP) 13 May 1987 -----	

2

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
WO 9726393	A	24-07-1997	JP	9202690 A	05-08-1997
DE 4414947	A	31-08-1995	IT	RM940778 A	16-06-1995
			JP	2700773 B	21-01-1998
			JP	7257991 A	09-10-1995
			US	5487354 A	30-01-1996
US 5474020	A	12-12-1995	US	5607507 A	04-03-1997
GB 2182262	A	13-05-1987	JP	62105998 A	16-05-1987
			AT	289086 A	15-01-1996
			AU	597599 B	07-06-1990
			AU	6455086 A	07-05-1987
			CA	1336061 A	27-06-1995
			CN	1016191 B	08-04-1992
			DE	3637006 A	07-05-1987
			DK	518486 A	01-05-1987
			FR	2589489 A	07-05-1987
			NL	8602738 A	18-05-1987
			SE	8604627 A	01-05-1987